Sealing Solutions



COMPOUND DATA SHEET FM140/0 Grey

General description

FM140/0 is a is a chlorobutyl compound with silicate filler. Unconventionally cured

Identification as per Ph.Eur. 3.2.9., method A

A typical ATR-FTIR spectrum of a clean, cut surface of FM140/0 is enclosed on page 3.

Physical properties

| i ilysicai properties | |
|-----------------------------------------------------------------|---------------------------------|
| Hardness | 46 ± 5 °Shore A |
| ISO 7619-1 (1sec Indentation) | |
| Density | 1.323 ± 0.025 g/cm ³ |
| ISO 2781 | |
| Ash content | 45.5 ± 2.0 % |
| Internal method. Calc.4h@700°C | |
| Compression set | 32 % |
| ISO 815, (typical value) | |
| Modulus 100 | 1.3 N/mm ² |
| Internal method. 100mm/min, (typical value) | |
| Modulus 300 | 2.0 N/mm ² |
| Internal method. 100mm/min, (typical value) | |
| Elongation @ Break | 670 % |
| Internal method. 200mm/min, ISO 37 Dumb-bell 2, (typical value) | |
| Tensile Strength @ Break | 6.6 N/mm ² |
| Internal method. 200mm/min, ISO 37 Dumb-bell 2, (typical value) | |
| Water Vapor Transmission Rate | 0.06 g/m ² .24h |
| Mocon, 38°C,100%RH, 1.27 mm thickness, (typical value) | · · |
| Oxygen Transmission Rate | 71 cc/m ² .24h |
| Mocon, 38°C, 90%RH, 100% O2, 1.27 mm thickness, (typical value) | |

Compound ingredient declarations

FM140/0 is not made with natural rubber latex. Latex

Nitrosamines FM140/0 is not made with chemicals that are associated with

nitrosamine formation as per the ASTM F1313-90 list. FM140/0 is not made using Di(2-EthylHexyl) Phthalate **Phthalates**

(DEHP) or other phthalates.

BSE/TSE For the raw materials of FM140/0, certification confirming that

such products are either of vegetable origin or are manufactured in severe process conditions for inactivation of prions as described in the EMA/410/01-rev.3 and in the European Pharmacopoeia 5.2.8. "Minimizing the risk of transmitting Animal Spongiform Encephalopathy Agents" is

available

MBT FM140/0 is not made with 2-mercapto-benzothiazole (MCBT,

also named MBT), or any of its derivatives.

Heavy Metals FM140/0 fulfills the EC Guideline 94/62/EC for heavy metals

in packaging materials and the CONEG regulation on reduction of toxics in Packaging Law: "packaging components shall not contain more than 100 ppm of Pb, Cd, Hg, and

Chemical properties

Ph.Eur.3.2.9. : FM140/0 meets the chemical requirements for ISO 8871-1 Type I closures specified in Ph.Eur. 3.2.9, ISO

USP <381> 8871-1 and USP <381>.

Typical results are given in the table on page 2.

Typical UV spectra are enclosed on page 3.

Ph.Jap.7.03. : FM140/0 meets the chemical requirements

specified in Ph.Jap. 7.03.

Typical results are given in the table on page 2.

Note: Chemical testing is performed on non-post-treated standard test plates or products, prepared using representative process conditions.

Biocompatibility

USP <87><88>: FM140/0 is non-cytotoxic and meets the ISO 10993-5 requirements of the Elution Test as described in Ph.Jap.7.03. USP <87>,"Biological Reactivity Tests, in vitro" and

the ISO 10993-5 "in vitro cytotoxicity". A typical test

certificate is enclosed on page 4.

ISO 10993-5 cytotoxicity testing is considered equivalent with Pharm. Jap. 7.03 cytotoxicity

testing.

Note: "FMxxx" refers to the type of compound, the extension "/x" refers to the color of the said compound. Differently colored compounds might be used for testing throughout this document. It is generally accepted that the color is irrel evant for the properties discussed, except Ash content and Density which are different per color.

Team Leader R&D lab Senior Manager Material Development Manager Regulatory Affairs Date

Valid from: September 14, 2015

Sealing Solutions



COMPOUND DATA SHEET FM140/0 Grey

Typical results of chemical properties as per the Ph.Eur.3.2.9., ISO 8871-1 and the USP <381> for FM140/0:

| Character | | Limits | | FM140/0 |
|------------------------------------------------|-----------|---------------------------------------------------------------------------------------------------------------------------------------------|--------|---------|
| Appearance of solution | Turbidity | Type I: ≤ 6 NTU (*) Type II: ≤ 18 NTU (*) | | 0 |
| Appearance or solution | Color | Solution S is not more intensely colored than reference | | Pass |
| Acidity or alkalinity (NA : Not applicable) | | ≤ 0.8 ml 0.01M HCl | EP | NA |
| | | | USP** | NA |
| | | ≤ 0.3 ml 0.01M NaOH | EP | 0.1 |
| | | | USP** | 0.0 |
| UV Absorbance (max 220-360 nm) | | Type I: ≤ 0.2 Type II: ≤ 4.0 | | 0.0 |
| Reducing substances | | Type $l: \le 3.0 \text{ ml } 0.01\text{M Na}_2\text{S}_2\text{O}_3$ Type $ll: \le 7.0 \text{ ml } 0.01\text{M Na}_2\text{S}_2\text{O}_3$ | | 0.2 |
| Extractable heavy metals | | 10 mm Bl2+ | EP | Pass |
| | | ≤ 2 ppm Pb ²⁺ | USP*** | Pass |
| Extractable zinc | | ≤ 5.0 ppm Zn ²⁺ | | 0.3 |
| Ammonium | | ≤ 2 ppm NH₄ ⁺ | | Pass |
| Residue on evaporation (only for EP) | | Type I: ≤ 2.0 mg Type II: ≤ 4.0 mg | | 0.1 |
| Volatile sulphides | | Any black stain on the paper is not more intense than that produced by a control solution | | Pass |

^(*) By definition corresponding with reference suspensions II and III (for Ph.Eur.) or B and C (for USP) respectively (**) Corrected with blank (***) Measured as per USP <231>; USP <231> will become obsolete by Dec 1, 2015

Typical results of chemical properties as per the Ph.Jap.7.03 for FM140/0:


| Characteristic | | Limits | FM140/0 |
|-------------------------------------|-------------|-----------------------|---------|
| Appearance | %T at 430nm | ≥ 99.0% | 99.6 |
| | %T at 650nm | ≥ 99.0% | 99.8 |
| pH (difference with blank) | | -1.0≥ ≤ 1.0 | -0.1 |
| Zinc | | ≤ 1 ppm Zn²+ | 0.4 |
| Reducing substances | | ≤ 2.0ml 0.002 M KMNO4 | 0.7 |
| Residue on evaporation | | ≤ 2.0mg | 0.2 |
| UV absorbance (Max. Abs. 220-350nm) | | ≤ 0.20 | 0.02 |
| Cadmium* | | ≤ 5 ppm | 0.01 |
| Lead* | | ≤ 5 ppm | 1.10 |

^(*) measured directly on the rubber





COMPOUND DATA SHEET FM140/0 Grey

Typical ATR-FTIR spectrum of a clean, cut surface of FM140/0:



Typical UV spectrum of the Solution S extract of FM140/0, measured as per the Ph.Eur. 3.2.9., ISO8871-1 and USP <381> (left) and Ph.Jap.7.03 (right):







COMPOUND DATA SHEET FM140/0 Grey

USP<87> Elution Test certificate for FM140/0:



TEST RESULT REPORT N°:10-B0277-N1



Sponsor:

TE 10118

Study Number: 10-B0277-N1 18/02/2010 Report Date:

Contact:

Helvoet Pharma Belgium NV Mrs. Nadia Nouri Industrieterrein Kolmen 1519

Date Sample Arrival: Technical Initiation:

10/02/2010

Address:

3570 Alken, Belgium

Technical Completion:

15/02/2010 18/02/2010

PB1000518

| Study | Elution Test - ISO | Temp/Time | 37°C/24 hours | |
|-----------|--------------------|-----------|---------------|--|
| Test Item | FM140/0 V9025 SAF1 | Ratio | 25cm²/20mL | |
| Lot | 30194939 | Vehicle | MEM-Complete | |

REFERENCE: According to "ISO 10993-5, 2009: Biological Evaluation of Medical Devices- Part 5:Tests for In Vitro Cytotoxicity." and "USP 32-NF 27, 2009: <87> Biological reactivity test, in vitro." Toxikon Reference: SOP 3.1.2.3, rev. 08

PROCEDURE: The biological reactivity of a mammalian monolayer, L929 mouse fibroblast cell culture, in response to the test item extract was determined. The samples and control articles were autoclaved prior to the preparation of the extracts. Extracts were prepared at 37±1°C for 24 hours in a humidified prior to the preparation of the extracts. Extracts were prepared at 37±1°C for 24 hours in a humidified atmosphere containing 5±1% carbon dioxide (static). Positive (natural rubber) and negative (silicone) control articles were prepared to verify the proper functioning of the test system. The maintenance medium on the cell cultures is replaced by the extracts of the test item or control article in triplicate and the cultures are subsequently incubated for 48 hours, at 37±1°C, in a humidified atmosphere containing 5±1% carbon dioxide. Biological reactivity was rated on the following scale: Grade 0 (No reactivity); Grade 2 (Mild reactivity), Grade 3 (Moderate reactivity) and Grade 4 (Severe reactivity). The test item is considered non-cytotoxic if none of the cultures exposed to the test item shows greater than mild reactivity (Grade 2).

OPINION AND INTERPRETATION: No reactivity (Grade 0) was exhibited by the cell cultures exposed to the test item at the 48 hours observation. Severe reactivity (Grade 4) was observed for the positive control article. The negative control article showed no signs of reactivity

OPINION AND INTERPRETATION: Based on the evaluation criteria mentioned above, the test

RECORD STORAGE: All raw data generated in this study will be archived at Toxikon Europe, according to SOP 4.2.8.

AUTHORIZED PERSONNEL

ir. Peter Cornelis Study Director

Vanessa Ruymen Quality Assurance

The test results on the enclosed report are only referring to the tested articles. Partly reproduction of this report can only be allowed after written permission of Toxikon. Toxikon guarantees that all results are acquired by testing according to officially accepted scientific methodology.

Toxikon Europe nv - Researchpark Haasrode 1724 - Romeinsestraat 12, B 3001 Leuven, Belgium - Tel. 32-16-40 04 84 - Fax 32-16-40 13 04 Fortis 230-0391575-06 KBC 431-0597001-33 - BTW/TVA BE 0442.395.719. - H.R. Leuven 80.154 - www.toxikon.be